















Grade	Brand name	Equivalent standard			Characteristics	Detailed information		
		JIS	AISI	WNo.		Special page	Brochure	Technical data
Type H13 & Modified (5Cr) Single melted	DHA1	SKD61	H13 eq.	1.2344 eq.	• General-purpose hot work die steel			
	DHA-WORLD	SKD61 mod.	H13 mod.	1.2344 mod.	• High hardenability & toughness			   
Type 2367 modified (5Cr) Remelted	DH31-S	-	-	1.2367 mod.	• High toughness • High strength at elevated temp.			
	DH31-EX	-	-	1.2367 mod.	• High hardenability & toughness • High strength at elevated temp.			 
Type SKD7 (3Cr-3Mo)	DH71	SKD7 mod.	-	-	• High softening resistance			
	DH32	SKD7 mod.	-	-	• High strength at elevated temp.			
Hot-Forging Die Steel	GFA	SKT4 mod.	L6 mod.	1.2714 mod.	• Especially for hammer forging			
	GF78	-	-	-	• 40HRC Pre-hardened steel • High strength at elevated temp.			
High Speed Tool Steel Matrix Type	DRM1	-	-	-	• High toughness • Maximum hardness 58HRC			 
	DRM2	-	-	-	• High hardness & toughness • Maximum hardness 62HRC		